

## **ENDUTEX - REVESTIMENTOS TEXTEIS, SA**



## TECHNICAL DATA SHEET

**REFERENCE: PRINT MS 25 FR** 

**DESCRIPTION**: PVC DOUBLE COATED HIGH TENACITY POLYESTER SCRIM

**COMPOSITION**: 72 % PVC

28 % POLYESTER

**WIDTH**: 160 - 250 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.50	
TOTAL MASS (g/m²)	$250 \pm 25$	EN ISO 2286-2
FABRIC MASS (g/m²)	70 ± 7	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 100 T.: 90	EN ISO 1421
TEAR STRENGTH (daN)	L.: 20 T.: 15	DIN 53363
AVERAGE PERMEABILITY OF FABRIC TO AIR (l/m²/s)	6200	EN ISO 9237
OPEN AREA (%)	33	Internal
BURNING BEHAVIOUR	B1	DIN 4102

L-Along T-Across

<u>NOTE</u>: This technical data sheet is not legal binding and is based on average results from current production. Unless otherwise stated, values cannot be considered as minimum to be satisfied.

Purchaser is fully responsible for determining the product suitability for its intended application.

Technical details are subject to change without prior notice, so please contact our technical service for any additional information you may require.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2017.10.20	2	Classin	G3.

Doc. 0044/DF.0